

# Dentin Phosphophoryn Promotes Odontoblast Differentiation in vitro and Induction of Mineralized Matrix in vivo.

著者	Mohammad Ali Akbor Polan
学位名	博士（歯学）
学位授与機関	北海道医療大学
学位授与年度	平成25年度
学位授与番号	30110甲第256号
URL	<a href="http://id.nii.ac.jp/1145/00006630/">http://id.nii.ac.jp/1145/00006630/</a>

論 文 題 目

Dentin Phosphoryn Promotes Odontoblast Differentiation *in vitro* and  
Induction of Mineralized Matrix *in vivo*

平成 2 5 年度

北海道医療大学大学院歯学研究科

Mohammad Ali Akbor Polan

## ***Introduction***

Vital pulp therapy is the method for the treatment of reversible pulpitis (Tziafas et al., 2000). The ultimate goal of vital pulp therapy is to rapidly regenerate dentin of excellent quality by using an external agent that possesses novel properties such as biocompatibility and bioactivity. The calcium hydroxide-based agents have been considered as the gold standard of direct pulp capping materials (Iwamoto CE et al., 2006; Tuna D and Olmez A, 2008) for several decades because of the favorable effects such as antibacterial and hard tissue stimulation (Schröder U et al., 1985). However, these agents do not provide close adaptation to dentin and also do not promote consistent odontoblast-differentiation. Thus, clinical success rate of the therapy by using calcium hydroxide-based agents does not satisfy dental practitioners according to their desire.

Dentin phosphophoryn (DPP), a member of small integrin-binding ligand N-linked glycoproteins (SIBLING) family, is the most abundant of the non-collagenous polyanionic proteins in dentin. DPP contains numerous aspartic acids and phosphorylated serine residues that render this protein as nature's most acidic protein (Stetler-Stevenson and Veis, 1983; Sabsay et al., 1991). The molecule is called thus as it is considered to be "Phosphate carrier". Phosphorylation of all potential serine results in a highly negatively charged molecule and is a virtual sink for the binding of calcium ions. It has been reported that the RGD domain in DPP induces integrin mediated signaling events. Moreover, it has been also reported that activation of the MAP kinase signaling pathway occurs when human mesenchymal cells were stimulated with DPP.

The purpose of this study was to examine the effects of DPP on differentiation and mineralization of odontoblasts.

## ***Materials & Methods***

MDPC-23 was used in this study. This cell line is a rat odontoblast-like cells, which was provided by professor Nör, University of Michigan. The cells were seeded and maintained with Dulbecco's Modified Eagle's Medium containing 10% fetal bovine serum in a humidified

atmosphere of 5% CO<sub>2</sub> at 37°C. MDPC-23 was incubated in the presence of DPP with various concentrations 0.1, 1, and 10 µg/ml and without DPP as a control. The cell-morphology was evaluated using microscope and cells proliferation was evaluated by cell number counting. Next, we examined the mRNA expressions for odontoblast-related molecules such as Runt-related transcription factor 2 (Runx2), Dentin matrix protein-1 (DMP-1), Alkaline phosphatase (ALPase), Bone sialoprotein (BSP), Osteocalcin (OCN), Osteopontin (OPN) by RT-PCR and real-time PCR. Moreover, to evaluate the calcified nodule formation, the cells were incubated for 7 days with DPP and stained with 2% Alizarin-red S. Then, the nodule formation was observed with a microscope. ALPase activity was measured as the score of ALPase activity per amount of total protein contained in the cells, with a Lab Assay ALP kit.

To investigate calcification inducibility for DPP, we performed implantation experiments in vivo. We combined 1 mg DPP with 5 mg collagen scaffold. Then DPP-collagen was adsorbed with rat dental pulp cells (RPCs) at  $1 \times 10^5$  in number. After 14 days incubation, the DPP-collagen-RPCs were implanted at dorsal site of the rat. The rats were sacrificed at 14 days after implanting. Then, hematoxylin and eosin-stained sections for the specimens were prepared according to the general method. Statistical analysis was performed using Tukey-Kramer.

## **Results**

### ***Cell morphology and proliferation evaluation***

According to the observation, it was found that the addition of DPP did not affect proliferation or morphology of MDPC-23.

### ***DPP induced osteoblast/odontoblast gene markers***

We assessed the expression of several osteoblast/odontoblast gene markers in response to DPP treatment in cells. The mRNA expression of DMP1 and ALPase in MDPC-23 was promoted by 0.1, 1 and 10 µg/ml DPP at 3 days (Fig. 3). The mRNA expression of osteorix, OCN and BSP was promoted by 1 and 10 µg/ml DPP at 3 days. Moreover, mRNA

expression of Runx2 and OPN was promoted by 10µg/ml of DPP. There was no change in the mRNA expression of Type I col by the stimulation with DPP.

#### ***DPP increased ALPase activity in MDPC-23***

To further examine the function of DPP in osteogenic lineage progression, we examined ALPase activity, which is a common pheno-typic marker for osteogenesis. ALPase activity was measured over a time course of 3, 5 and 7 days. We observed the high ALPase activity in MDPC-23 was induced by 1 and 10 µg/ml of DPP at 5 and 7 days compared to the control (p<0.05).

#### ***DPP increased calcium deposition in MDPC-23***

When MDPC-23 cells were cultured with differentiation medium containing 1 and 10 µg/ml DPP, increased Alizarin red S staining (Fig. 5A) and on quantitative analysis, the number of mineralized nodules was increased at 7 days, as compared to controls (p<0.05). Moreover, a similar trend was observed for alizarin red S staining, without the addition of differentiation medium containing 0.1, 1 and 10 µg/ml of DPP, increased Alizarin red Staining and on quantitative analysis, the number of mineralized nodules was Increased at 7 days, as compared to controls (p<0.05).

#### ***Implantation of collagen-RPCs with DPP in rat***

In order to investigate mineralized-matrix inducibility for DPP, we performed implantation experiments *in vivo*. Mineralized tissue-like matrix formation was induced by composites of DPP-collagen and RPCs, and rapid degradation of collagen was observed, as compared to controls, at 14 days after implantation into dorsal sites in rats (Fig. 6). Moreover, there was absence of inflammatory cells in the HE staining.

#### ***Discussion***

DMP-1 is a member of SIBLING family and a specific marker of dentin. In this study,

DMP-1 showed the increased expression in the presence of DPP. Moreover, DPP also promoted the mRNA expression of Runx2, osteorix and OCN after binding to integrin receptor on the cell surface via its RGD domain. It was speculated that these phenomenon were caused by activating the MAPK signaling pathways that culminate in a nature osteogenesis. ALPase gene expression was also promoted in the presence of DPP, validating ALPase activity assay result. This study demonstrates that DPP promotes the odontoblast differentiation and mineralization *in vitro* and that DPP induces the formation of hard-tissue like matrix and also promotes bio-degradability of the scaffold *in vivo*. From these results, it can be speculated that DPP is crucial to be an excellent biomaterial. Further investigation is required to elucidate the detail properties of DPP as a promising molecule for odontogenesis.

The findings suggested that DPP promotes the differentiation and mineralization of odontoblasts. Therefore DPP can be a promising candidate for formulating a new pulp capping material.

### ***References***

- Iwamoto CE, Adachi E, Pameijer CH, Barnes D, Romberg EE and Jefferies S .Clinical and histological evaluation of white ProRoot MTA in direct pulp capping. Am J Dent 2006; 19:85-90.
- Sabsay B, Stetlaer-Stevenson WG, Lechnner J H and Veis A. Domain structure and sequence distribution in dentin phosphophoryn. Biochem J 1991; 276, 699-707.
- Schröder U. Effect of calcium hydroxide-containing pulp-capping agents on pulp cell migration, proliferation, and differentiation .J Dent Res 1985:541-548.
- Stetler-Stevenson W G and Veis A. Bovine phosphophoryn: Composition and molecular weight. Biochem .1983; 22, 4326-4335.
- Tuna D and Olmez A. Clinical long-term evaluation of MTA as a direct pulp capping material in primary teeth. Int Endod J 2008; 41:273-278.